

Materials & Conversions

Toggles

Rockers

Pushbuttons

Programmable

Keylocks

Rotaries

Slides

Tactiles

Tilt

Touch

Indicators

Accessories

Supplement

Z

PLASTICS

Specific Name	Acronym or Abbreviation	Generic Name
Acrylonitrile butadiene styrene	ABS	Shatterproof thermoplastic composed of styrene and acrylic resin; ABS provides resilience, shiny appearance, and stable base for metal plating
Carbon blended polyamide		Polyamide blended with carbon for antistatic property
Carbon composite polyacetal		Polyacetal
Diallyl phthalate	DAP	Diallyl phthalate; a thermosetting resin
Ethylene Propylene Terpolymer	EPT	Ozone resistant plastic
Glass fiber reinforced diallyl phthalate	GFR DAP	Diallyl phthalate
Glass fiber reinforced polyamide	GFR PA	Polyamide
Glass fiber reinforced polybutylene terephthalate	GFR PBT	Polyester
Liquid crystal polymer	LCP	Liquid crystal polymer
Nitrile butadiene rubber	NBR	NBR; mainly used where oil-proof is required
Phenolic resin		Phenol plus aldehydes; used extensively as thermosetting plastic
Polyacetal		Polyacetal
Polyamide	PA	Nylon 6/6; Polyamide; always a nylon resin
Polybutylene terephthalate	PBT	Polyester
Polycarbonate	PC	Lexan; Polycarbonate; damaged by trichloroethylene solvent and so changes to polyamide
Polyethylene	PE	Polyethylene
Polyphenylene sulfide	PPS	Polyphenylene sulfide
Polyoxymethylene	POM	Polyoxymethylene
Polypropylene	PP	Polypropylene; more elastic than polycarbonate
Polyvinyl chloride	PVC	Polyvinyl chloride; loses pliability below 0°C (32°F)
Resin		Polymer
Silicone		Silicone

ELEMENTS

Ag	silver	Cr	chromium	Pb	lead
Al	aluminum	Cu	copper	Sn	tin
Au	gold	Ni	nickel	Zn	zinc

TEMPERATURE

Fahrenheit			°C	°F	°C	°F
Thermometric scale with fixed points marked 32°F for freezing point and 212°F for boiling of water.	(Fahrenheit - 32) × .555 = Celsius	-40	-40	0	+32	
Celsius	(Celsius × 1.8) + 32 = Fahrenheit	-30	-22	+50	+122	
International thermometric scale with fixed points marked 0°C for freezing point and 100°C for boiling of water.		-25	-13	+55	+131	
		-20	-4	+70	+158	
		-10	+14	+85	+185	
				+100	+212	

LINEAR DIMENSIONS

Formulas for Conversion millimeter x .03937 = inch inch x 25.4 = millimeter	Fraction	Inch	Millimeter	Fraction	Inch	Millimeter
		.100	2.54		.394	10.0
		.150	3.81	15/32	.469	11.9
		.197	5.0		.472	12.0
		.236	6.0	1/2	.500	12.7
	1/4	.250	6.35			

FORCE

Formulas for Conversions			Formulas for Conversions		
ounce•force	x .2780139	= newton	kg/cm	x 2.2046	x .3937 = lb/in
pound-force	x 4.4482220	= newton	newton•meter	x .7375621	= pound-foot
kilogram-force	x 9.8066500	= newton	newton•meter	x .1019716	= kilogram-meter
newton	x .1019716	= kilogram-force	newton•meter	x 141.6119	= ounce-inch
newton	x .2248089	= pound-force	newton•meter	x 8.8507	= pound-inch
newton	x 3.5969420	= ounce•force	pound-foot	x 1.355818	= newton•meter

PLATING THICKNESS

Micron One millionth of a meter; a micrometer	1 micron = 1 thousandth of 1 millimeter 1 micron ÷ .0254 = 39.37 millionths of an inch Example: 3 microns ÷ .0254 = 118.11 millionths of an inch	1 gram = .03527 ounce 1 kilogram = 35.27 ounces 1 kilogram = 2.2 pounds	1 ounce = 31.10348 grams 1 ounce = .03110348 kilogram 1 pound = .4539 kilogram
---	--	---	--